

**SECTION 13070**  
**BULLET RESISTANT FIBERGLASS**  
**UL752 LEVEL IV**  
**(BGAA-04)**

**PART 1 GENERAL**

1.1 REFERENCE

The publications listed below form a part of this specification. UNDERWRITERS LABORATORY UL, Standards for Bullet Resisting Equipment.

1.2 SUBMITTALS

The following shall be submitted in accordance with Sections 01340 and the SPECIAL CONTRACT REQUIREMENTS: Submit for approval prior to fabrication samples, brochures, specifications, UL Listing and UL752 Current Test Results as provided by Underwriters Laboratory, and printed data in sufficient detail to indicate compliance with the contract documents. Manufacturer's instructions for installation of Bullet Resistant Fiberglass.

1.3 DESIGN

Through the design, manufacturing technique and material application the Bullet Resistant Fiberglass shall be of the "non ricochet type". This design is intended to permit the encapture and retention of an attacking projectile lessening the potential of a random injury or lateral penetration.

1.4 DELIVERY, STORAGE AND HANDLING

Deliver the materials to the project with the UL Listed Labels and the manufacturer's UL752 designation labels intact and legible. Handle the material with care to prevent damage. Store the materials inside under cover; stack flat and off the floor.

1.5 WARRANTY

All materials and workmanship shall be warranted against defects for a period of 5 (five) years from the date of receipt at the project site.

**PART 2 PRODUCTS**

## 2.1 BULLET RESISTANT FIBERGLASS MATERIAL

The panels shall be made of multiple layers of woven roving ballistic grade fiberglass cloth impregnated with the thermoset polyester resin and compressed into flat rigid sheets. The production technique and materials used shall provide the controlled internal delamination to permit the encapture of a penetrating projectile. Bullet Resistant Fiberglass panel: 1-3/8" maximum thickness, and 14.5 pounds per square foot maximum weight. Material shall be Bullet Guard Architectural Armor (BGAA-04), by Bullet Guard Corporation, West Sacramento, CA, Phone (916) 373-0402, Fax (916) 373-0208, email: [sheila@bulletguardmail.com](mailto:sheila@bulletguardmail.com), Website: [www.bulletguard.com](http://www.bulletguard.com)

## 2.2 SECURITY LEVEL

The Bullet Resistant Fiberglass will be UL Listed and Tested for UL752 Level IV.

## 2.3 FIRE RATING

(BGAA-04) Has a one-hour fire rating per ASTM E119-98 and can be used for fire corridors and firewalls.

# **PART 3 EXECUTION**

## 3.1 SUPPORTING MEMBERS

Prior to installing the bullet resistive material the contractor shall verify that all supports have been installed as required by the contract documents and the architectural drawings.

## 3.2 JOINTS

All joints shall be reinforced by a back-up layer of bullet resistive material. The bullet resistance of the joint, as reinforced, shall be at least equal to that of the panel. Minimum width of reinforcing layer at joint shall be 4-inches (2" on each panel or a 2" minimum overlap).

## 3.3 APPLICATION

Armor shall be installed in accordance with the manufacturer's printed recommendations. Armor panels shall be adhered using an industrial adhesive, mastic, screws or bolts. Method of application shall maintain the bullet resistive rating at junctures with the concrete floor slab, the concrete roof slab, the bullet resistive doorframes, the bullet resistive window frames, and all required penetrations.

**\*\*End of Section\*\***